Quantitative Method for Comparative Assessment of Particle Filtration Efficiency of Fabric Masks

as Alternatives to Standard Surgical Masks for PPE

Amy V. Mueller[1], Matthew J. Eden[2], Jessica M. Oakes[2], Chiara Bellini[2], and Loretta A. Fernandez[1*]

[1] Departments of Civil and Environmental Engineering and Marine and Environmental Sciences

Northeastern University, Boston, MA 02115

[2] Department of Bioengineering, Northeastern University, Boston, MA 02115

*corresponding author and lead contact l.fernandez@northeastern.edu

Conceptualization, L. A. F. and A. V. M; Methodology, , L. A. F. and A. V. M; Formal Analysis, A. V. M.

and C. B.; Investigation, L. A. F., A. V. M., M. J. E., J. M. O., and C. B., Writing – Original Draft, L. A. F.

and A. V. M.; Writing – Review & Editing, A. V. M., C. B., and L. A. F.

Summary

In response to the COVID-19 pandemic, cloth masks are being used to control the spread of virus, but the

efficacy of these loose-fitting masks is not well known. Here, tools and methods typically used to assess

tight-fitting respirators were modified to quantify the efficacy of community- and commercially-produced

fabric masks as PPE. Two particle counters concurrently sample ambient air and air inside the masks;

mask performance is evaluated by mean particle removal efficiency and statistical variability when worn

as designed and with a nylon overlayer, to independently assess fit and material. Worn as designed both

commercial surgical masks and cloth masks had widely varying effectiveness (53-75% and 28-90%

filtration efficiency, respectively). Most surgical-style masks improved with the nylon overlayer, indicating

poor fit. This rapid testing method uses widely available hardware, requires only a few calculations from

collected data, and provides both a holistic and aspect-wise evaluation of mask performance.

1. Introduction

In response to the critical shortage of medical masks resulting from the COVID-19 pandemic, large

portions of the population are mobilizing to produce cloth masks using locally-sourced fabrics. While the

general population is being advised to wear masks to protect others from virus that may be spread from

the wearer, the efficacy of these masks as a means of protecting the wearer from airborne particles

carrying virus is also a concern, particularly as medical masks grow scarce. This issue may become more

critical if it becomes necessary for medical care workers to use similar alternative personal protective

equipment,[1] but is already important for individuals who may be caring for a household member who is ill

or who may be in a high-risk category for complications.[2]

The effectiveness of masks to protect wearers from airborne particles is known to be a function of both

materials and fit. Standard methods to test the performance of respirators and masks designed to form a

seal against the face, such as N95 respirators, assume that appropriate high-filtration materials have

been used in the construction of the masks and therefore employ instruments that test the fit by

comparing the concentration of particles in air inside and outside of the mask while the subject moves

his/her head through a series of positions.[3] Several instruments have been specifically designed to

perform these tests (e.g., the TSI PortaCount), simplifying the testing process for users by reporting a

single metric of "fit" (i.e., Fit Factor = ratio of time-averaged particle concentration outside and inside

mask). In contrast, standard methods for surgical masks focus exclusively on testing the materials and do

not provide for a measurement of the mask as constructed or as worn.[4-7]

Anticipating the need to produce face coverings from readily-available materials, several studies have

used these standard methods for materials testing to compare the filtration efficiency of materials such as

cotton t-shirts, sweatshirts, handkerchiefs, and towels with the filtration efficiency of materials used to

manufacture facepiece respirators (N95 masks) and surgical masks.[8-10] Further, tools developed for N95-

type masks have been applied directly to evaluate particle filtration for loose-fitting, surgical type masks.[11]

Generally, these studies have found that no commonly-available materials produce filtration efficiency

close to respirators such as N95s, with cotton cloth facemasks providing about half the protection (i.e.,

"Fit Factor" decrease by a factor of 2) of standard surgical masks against airborne particles.[11] Notably,

these previous studies are unable to pinpoint the problems with loose-fitting masks (i.e., separate out a

poor fit from poor materials used in the construction), though in other work an elastic layer (e.g., nylon

stocking) placed over the mask when worn has been found to improve filtration efficiency of loose-fitting

masks by minimizing air flow around the cloth layers.[12]

Importantly, it has been shown that head motions and positions do not significantly affect the performance

of loose-fitting masks in terms of filtering out nano-sized particles,[11] suggesting that a simplified mask

testing protocol (compared to the multi-step fit test used for respirators) may be sufficient for

characterizing particle filtration efficacy of loose-fitting masks. Given the highly varied results and

protocol shortcomings noted for prior studies,[13] development of a rapid and quantitative method for

evaluating potential PPE options would be of great value to the general public at this time.

The purpose of this work was to develop a standardized method to quantitatively assess the efficacy of

sewn fabric facemasks and standard surgical masks in terms of protecting the wearer from airborne

particulates of the size range potentially associated with viral transmission (<300 nm). This leverages

instrumentation designed for respirator fit testing, which is widely available nationally at health care

centers, fire departments, etc., but provides two key adjustments that improve the data quality for loose-

fitting mask testing. First, two instruments are used to simultaneously record high resolution (1 Hz)

particle concentration measurements in the room and behind the mask, enabling the method to be used

in cases where particle concentration may vary on the timescale of tests, in comparison to standard fit

testing which assumes consistent particle concentrations in the room over ~minutes and therefore

sequentially samples the ambient and in-mask air. Data recorded during experiments described below

show variability of particle concentrations by up to a factor of 2 over <1 minute, supporting the need for

this dual-instrument configuration if used more broadly, especially outside of specialized testing rooms.

Second, by conducting separate tests for masks worn loosely (as designed) and for the masks held close

to the face using a layer of nylon stocking (as recommended by Cooper et al.[12]), the method enables

independent evaluation of the mask fit and mask materials as they contribute to overall filtration

efficiency.

The proposed protocol enables testing of an individual mask design (n=3 masks for statistical analysis)

within ~30 minutes for systems with digital data collection, providing a rapid screening tool to test a

variety of mask designs produced from readily-available materials. This method can be easily replicated

in health care centers, fire stations, and other facilities nationally, to vet specific masks in near-real time.

To validate the methodology, this manuscript reports data collected from an initial set of commercial and

homemade masks, however results from ongoing tests are being updated regularly at a public web portal

as additional prototype masks are evaluated. Given the limited time and current social distancing

precautions, all tests were conducted while masks were being worn by the same subject, breathing

normally, through the nose, with the mouth closed, while holding the head at a steady position. Data

reported by van der Sande et al.[11] provide confidence that limitation of motions and positions does not

significantly limit the conclusions that can be drawn from the resulting data, and results from a single test

subject are used here primarily to validate the protocol itself.

2. Results and Discussion

The percent removal of particles (of size range characterized below, D<300 nm) for each mask was

computed from data collected each second over one minute tests; examples of the high resolution data

collected for each test are provided in Figure 1 for a well-fitted N95 mask (N95-1) and a surgical-style

cloth mask (CS-1). The breathing pattern of the wearer can be observed as oscillations in the "inside

mask" data, and the issue of variability in ambient particle concentrations over a 1-minute test is clearly

visible in the top panel.

Figure 1: Particle concentrations in the room (red squares) and inside the mask (green triangles) with calculated removal percentage (blue circles) vs. time for a single one-minute test of a well-fitted N95 mask (N95-1, top) and an example cloth surgical-style mask (CS-1, bottom). Time-based variability in filtration efficiency corresponds to the breathing patterns of the mask wearer (inhales vs. exhales). As expected, the N95 mask has high and consistent filtration efficiency ($\bar{x}$=99.0 %, s_t=0.75 % for this single test). The cloth surgical-style mask has both lower filtration efficiency and higher variability ($\bar{x}$=53.0 %, s_t=10.5 % for this single test).

From these data, one can extract both mean removal efficiency and a measure of time-based variation ($\bar{x}$

and s_t, as defined below), which each provide information on mask performance. It is observed that $\bar{x}$ and

s_t are inversely correlated (Figure 2), wherein an improved fit generally leads to both higher mean particle

removal efficiency and lower time-based standard deviation (consistency in particle removal),

independent of the materials being used.

Figure 2: Improving mask performance through better fit and filtration materials leads both to increased
mean particle removal efficiency and decreased variation in filtration over time; data shown for masks
worn as designed.

Data collected with the subject wearing the nylon overlayer alone had $\bar{x}$=7.0% ± 2.5% (standard deviation

calculated from n=3 replicates) with s_t=18%; it is concluded therefore that the overlayer itself does not

provide significant filtration capacity and in the following discussion it is considered primarily to improve

the snugness of fit of the underlying mask.

The method is first evaluated through analysis of available commercial masks (Figure 3), including N95

respirators, surgical masks marketed for medical use, and other (in this case, a surgical-style mask with a

charcoal-embedded layer marketed for persons with allergies or wearing while exercising in areas with

high levels of air pollution). Blue bars show mean particle filtration for masks worn as designed, while

gray bars provide a proxy for best possible fit by adding the nylon overlayer. Differences between blue

and gray bars provide a measure of the looseness of the fit (extent of leakage of air around the mask in

normal wear) while gray bars provide a measure of filtration capacity of the mask material.

Figure 3: Particle filtration efficiency of standard commercial masks of 3 types: N95 (N95-n), surgical
style marketed for medical use (S-n), and Other (O-1, a charcoal filter mask). Data collected with a nylon
overlayer holding the mask in place represent a proxy for best-possible fit, i.e., gray bars provide a
measure of the filtration capacity of the materials. N95-1 was well-fitted to the mask wearer and shows
the expected >99% filtration, while N95-2 was less well fitted, as seen by the difference between the blue
and gray bars. While the fit of the three surgical masks (S-1 to S-3) is quite different (blue bars), the
materials are comparable (gray bars). Error bars show standard deviation between replicates (n=3 masks
for each type tested).

As expected, the mean removal efficiency for the well-fitted N95 mask (N95-1) is greater than 99% with

very low variability between replicates (s=0.36%) and low time-based standard deviation (s_t=0.78%, see

Figure 2 data point with highest filtration efficiency). This corresponds to a Fit Factor ($C_{outside}/C_{inside}$) of

126, which is above the minimum passable standard of 100,[14] however presentation of results as mean

and variability provides more information on the range of particle filtration efficiencies experienced by the

user. The poorly-fitted N95 mask (N95-2) has a lower mean removal efficiency ($\bar{x}$=90.6%), higher

variability between replicates (s=5.9%), and higher time-based standard deviation (s_t=4.6%). This

corresponds to a fit factor of 10.6, which is below the minimum passable standard.

In comparison, the standard medical-type masks (S-1 to S-3), when worn over the chin and with an

adjusted nose wire, had a mean removal efficiency of only 50 to 75% when worn as designed. In

comparison, when tightly fitted to the face using a nylon overlayer these masks achieve from 86 to 90%

mean removal efficiency, indicating that (1) the material can actually provide much better filtration than is

achieved in normal wear and (2) differences between brands are primarily in the quality of fit rather than

the quality of material used. Interestingly, in this case the carbon filter mask (O-1) performs approximately

as well as the best performing surgical mask despite a significant difference in the design specifications

and materials used.

The same measurements and metrics were then used to test fifteen different cloth masks being made or

marketed to the public at this time (April-May 2020). Results (Figure 4) are presented as absolute particle

removal efficiency (top panel) and in comparison with the top performing surgical mask (S-1) (bottom

panel). While these masks represent a small subset of available masks and materials, several useful

preliminary observations can be made.

Figure 4: Performance of a range of cloth masks being made by the community and by commercial vendors presented as absolute performance (top panel) and in comparison to S-1, the top performing surgical mask (bottom panel). Preliminary data show the difference between performance of masks using different form factors, e.g., cone-shaped masks appear to have a better and more consistent fit to the face. Notably multiple cloth masks perform as well as or better than surgical masks when worn as designed, and some provide equivalent filtration to surgical masks snugged to the face. However, there is wide variability in filtration provided by cloth masks, due both to fit (difference between blue and gray bars) and materials (gray bars).

First, quality of cloth masks is highly variable, both in fit (difference between blue and gray bars) and

material filtration capacity (gray bars); therefore the public would greatly benefit from a quantitative

method for evaluating masks they may be considering for health protective reasons. Second, it appears

that different masks shapes may provide a more consistent fit even when hand-made using standard

patterns; e.g., in these data the cone masks appear generally to fit better than the surgical-style masks

(as evaluated by difference between blue and gray bars, where addition of the nylon layer generally

improved performance for surgical-style masks but not for cone-shaped masks). Exceptions to

improvement when adding the nylon overlayer were rare and due to material stiffness where the mask

could not completely conform to the wearer's face and therefore the nylon layer led to bunching (creation

of new air leakage pathways). The nylon layer also reduced the variability with time as indicated by a

decrease in the time-based standard deviation. Both of these metrics indicate improved protection for the

wearer from particle inhalation.

When using mask S-1 worn as designed as a baseline, several of the cloth masks match or exceed this

performance (Figure *4*, bottom panel). The masks that achieved this level of filtration without the stocking

overlayer were cone shaped and included a layer of meltblown filter fabric, similar to interfacing layers

being added to many homemade masks, and specified as BFE85, between fabric cover layers. Additional

filter layers including water-repellent non-woven cloth marketed as disposable massage table covering

and dry disposable baby wipes, improved the filtration efficiency only moderately in the cone shaped

masks. Surgical-style masks that achieved the best filtration efficiency with the addition of a nylon

overlayer included a filter layer (organic cotton batting, Pellon, or loosely-woven cotton muslin) between

two layers of cotton fabric. These data are not included here due to limited number of replicates, but are

available on a web portal (SI).

3. Conclusion

A rapid testing protocol is presented for evaluation of loose-fitting type masks to provide quantitative,

intercomparable data for particle removal efficacy of masks made with different types of fabrics and with

different designs/fits, independently providing an assessment of the quality of the mask fit and the

material used. The protocol collects high-resolution particle count data inside and immediately outside of

masks to report both mean and time-based standard deviation of particle removal efficiency, while

wearing the mask as-designed and under a nylon layer that snugs the mask to the face. The protocol is

validated on a well-fitted N95 mask, and a commercial surgical-type mask is used as a reference baseline

for evaluation of alternative mask particle removal efficiencies. Commercial surgical masks marketed for

medical use had mean particle removal efficiencies from 50-75% when worn as designed but up to 90%

when snugged to the face under a nylon layer. Cloth masks tested had widely varying mean particle

removal efficiencies (<30% to near 90%), with some cloth masks achieving similar filtration efficiencies as

commercial surgical masks. However, in general, surgical-style cloth masks had poor fit (i.e., performance

was greatly enhanced with the nylon overlayer) compared to cone-shaped masks, and masks with good

material filtration performance tended to have a filter layer (e.g., meltblown BFE85 filter layer) in addition

to two layers of cotton or non-woven fabric.

This rapid testing method (~30 minutes per mask design including replicates for statistical validity)

provides a holistic evaluation of mask particle removal efficacy (material, design, and fit) while enabling

independent evaluation of these characteristics. This method uses instrumentation that is typically

available in many health centers and fire stations, as well as other facilities, and compensates for

assumptions made in fit-testing programs so that it can be easily replicated for on-site testing of specific

masks across many communities.

4. Experimental Procedures

Particle counters. Particles in ambient air and air inside of the mask breathing zone were counted using

two PortaCount Plus Model 8028 instruments running in count mode. The PortaCount Plus instrument

uses a condensation particle counter to determine particles per cm^3 in air sampled at a flow rate of 1.67

cm^3/s and reports one value (in particles/cm^3) each second.[15] The instrument counts particles ranging in

size from 0.02 to >1 μm, however data on the size distribution of counted particulates is not reported; size

distribution of the particles used to challenge the masks was therefore measured independently, as

reported in the following section.

Mask fit testing is usually conducted using a single instrument in fit test mode, which sequentially tests air

inside and outside the mask and therefore depends on an assumption of consistent particle concentration

in the room. As this assumption was frequently violated in our test setup even in cases where particle

generation was used (which may therefore commonly be the case in other facilities), here two PortaCount

instruments were used in count mode to simultaneously collect and display continuous data for ambient

air and inside mask air at high frequency (1 Hz) during minute-long tests.

Figure 5: Test setup has two PortaCount systems running in parallel; 1/8" diameter tubing of identical
length connects (top) the mask port to one instrument sampling port and (bottom) a tube inlet located just
outside the mask to the second instrument sampling port. Both instruments are run in "Count" mode
where concentrations are reported once per second (1 Hz). The dual-instrument configuration is required
because each instrument has only one internal measurement cell, for which the input is swapped
between the sampling and ambient inputs during standard fit testing. Photograph of PortaCounts used,
including ports and tubing available in SI (Figure S1).

Two 1/8" ID tubes (sold with the PortaCount Instrument) trimmed to equal length (approximately 100 cm)

sampled air just inside and outside of the mask. Air inside the mask was sampled through a tight-fitting

grommet inserted into each mask using a TSI Fit Test Probe Kit (model 8025-N95) and positioned at the

philtrum of the upper lip per standard mask testing guidance appropriate to the shape of each mask.

Ambient air was sampled from a position ~3 cm from the grommet on the outside of the mask.

Particle Generation and Characterization. All tests were run in a 65 m^3 rectangular room after at least

15 minutes of operating a TSI Particle Generator Model 8026 (TSI Incorporated, Shoreview, MN, USA).

This tool is typically used in conjunction with TSI PortaCount instruments to ensure sufficiently high

particle counts and appropriate size distributions to meet OSHA standards. Particles were generated from

a dilute (2%) solution of sodium chloride (NaCl), reported to have a nominal size of 40 nm with a

geometric standard deviation of 2.2 based on instrument specifications.[16] To verify that the particles

challenging the masks was comprised primarily of these generated particles, the particle size distribution

in the room was characterized by running three 5-minute tests approximately hourly on several testing

days (n=21 in replicates of 3) using the TSI Engine Exhaust Particle Sizer Spectrometer (EEPS) Model

3090 (for particles in the range 5.6 to 560 nm, with 32 channels acquired at 10 Hz) and the TSI Optical

Particle Size Spectrometer (OPS) Model 3330 (for particles in the range 0.3 to 10 μm, with 16 channels

acquired at 1 Hz). The size distribution of particle number concentration was consistent at all times and

days sampled, which supported the averaging of collected data. The histogram of average normalized

particle frequency revealed a bimodal distribution of particle sizes, shown in Figure 6. Confidence

intervals (CI) for the count median diameter (CMD) and the geometric standard deviation (GSD) were

calculated from Student's t-test statistics, with p=0.05 and M=20 degrees of freedom. The first peak likely

represents particles that are not filtered by building HVAC systems, as the distribution parameters

(CMD=9.53 ± 2.19 nm, GSD=1.23 ± 0.13; average ± 95% CI) are consistent with background air

measurements reported by the authors in other rooms and buildings on campus.[17] Features of the second

peak (CMD = 37.30 ± 15.40 nm, GSD = 1.79 ± 0.44) are in agreement with specifications reported for the

TSI Particle Generator manual. Overall, 97.01 ± 0.02% (average ± 1•s) of particles are in the standard

range used to challenge masks (<300 nm), so the reported particle filtration efficiencies can be directly

compared to numbers reported to comply with OSHA standards.

Figure 6: Average histograms of normalized particle frequency as a function of size, with superimposed
bimodal lognormal distribution. Count median diameter (CMD ± 95% CI) is 9.53 ± 2.19nm for the first
peak and 37.30 ± 15.40nm for the second peak. Geometric standard deviation (GSD ± 95% CI) is 1.23 ±
0.13 for the first peak and 1.79 ± 0.44 for the second peak. Particles generated by the TSI Particle
Generator account for the larger peak, while particles in lab air account for the smaller peak.

Calibration. An inter-calibration was conducted between the two PortaCount modules to account for any

drift or changes in calibrations due to, e.g., wick saturation. Each sampling day, calibration data (a

minimum of three one-minute time series, n=180) were collected by recording readings simultaneously on

both instruments while sample tubes were side-by-side (within 3 cm), open to the air (no mask), and a

minimum of 1m from any person and 2m from the particle generator (as recommended by the

manufacturer). Correlation coefficients between the readings from the two instruments were consistently

above 0.9, and day-specific linear regressions were used to normalize particle counts from the Reference

PortaCount to equivalent particle counts from the Mask PortaCount before calculating particle removal

efficiencies.

Data collection and processing. Each mask test consisted of three one-minute runs while wearing the

mask as designed (Figure 7 (a)). In addition, the mask material was held against the face by adding a

section of nylon stocking over the entire mask area following recommendations from Copper et al.[9]

(Figure 7 (b)) to simulate best possible fit and provide information on material filtration, and a single one-

minute test was recorded in this configuration. All masks except the well-fitted N95 were tested in this

second configuration. Results are reported only for masks for which at least three replicate sample masks

were available (data for masks with n<3 are being provided through our web portal).

Particle concentration data from inside and outside the mask was logged each second for the one minute

tests using video capture and subsequently transcribed to a database (noting that newer PortaCount

models can log count data through a software interface to simplify data collection). Particle removal at

each time step was calculated as follows:

312                  $\% \ particle \ removal = PPR = \frac{C_{outside} - C_{inside}}{C_{outside}} \times 100$ (1)

where $C_{outside}$ is the corrected reading from the Reference PortaCount (as described above) and C_{inside} is

the reading in the breathing zone of the mask.

Average particle removal efficiency ($\bar{x}$, reported as % removal), standard deviation between masks

(generally n=3, **s** reported as %), and mean standard deviation over the one-minute tests (**s$_t$**, reported as

%) were computed for each mask with and without a nylon stocking layer. These summary statistics can

be used to calculate Fit Factor for the masks, if desired, using Eqn. 2:

322                  $Fit \ Factor = \frac{C_{outside}}{C_{inside}} = \frac{1}{1 - PPR/100}$ (2)

Figure 7: Facemask (Mask CS-1) worn as designed **(a)** and with a nylon stocking layer **(b)** with tightly-
sealed grommet positioned at the philtrum of the upper lip. The grommet is used to sample air from inside
the mask during testing. Note: this mask could have been worn inside-out to ensure the folds faced down.
However, for the purposes of this test precautions against particle collection in folds were not considered
necessary.

Masks. Masks tested are given labels according to the mask type and then an individualized sample

number. Commercial masks are divided into N95-type (N95-1, N95-2, etc.), surgical-style (S-1, etc.), and

other (O-1, etc.). Cloth masks are given a pre-pended "C" identifier and divided into surgical-style (CS-1,

etc.), cone-shaped (CC-1, etc.), and duck-bill shaped (CD-1, etc.) (Figure S2). Results are reported for a

range of commercially-produced, medical-type facemasks (masks with elastic ear loops and in-sewn

wires to adjust fit to the bridge of the nose), and fifteen sewn fabric facemasks of various designs that

were sourced from community volunteers producing masks for essential personnel as well as online

vendors that have started to market masks of this type since March 2020 (Table S1). Several of the fabric

masks included filter layers such as non-woven polypropylene fabric, meltblown textiles, and disposable

baby wipes. In addition, several sewn masks included hydrophobic layers including interfacing (Pellon)

and non-woven fabric marketed as disposable massage table covering. Some masks included wires to fit

the masks across the bridge of the nose. A set of well-fitted (N95-1) and poorly fitted (N95-2) masks were

tested to validate the protocol.

Acknowledgements

Funding for this work was provided by Northeastern University Office of the Provost through a COVID-19

Seed Grant. Advice, materials, tools, instruments, and time were donated or shared with us in order to

carry out this project. A critical TSI PortaCount model 8028 was donated by Pfizer Inc. through the

coordination of Luanne Kirwin, Sonya Ross, Rob Silk, John Price, and Michael Glover. Tools, advice, and

expertise in conducting fit testing were generously provided by Gregory Lawless, TSI Incorporated; Albert

Thomas, the Massachusetts Department of Fire Services; George Mulholland, Department of Chemical

and Biomolecular Engineering, University of Maryland; Marco Fernandez, National Institute of Standards

and Technology; and John Price and Dan Meinsen, Environmental Health and Safety, Northeastern

University. Jessica Benedetto, Laurie Bowater, Jennifer Cawley, Benjamin Chung, Steve Gransbury,

Denise Hajjar, Michelle Kane, Laura O'Neill, Waas Porter, Stephanie Potts, John Price, Alan Raymond,

Renée Scott, and Mark Vera kindly donated masks. Data extraction was provided by dedicated

undergraduate students Matthew Biega, Alina Dees, Ariana Patterson, and Kelsey Walak. Thanks also to

Christine Trowbridge for assistance in editing.

References Cited

1. MacIntyre, C.R., Seale, H., Dung, T.C., Hien, N.T., Nga, P.T., Chughtai, A.A., Rahman, B., Dwyer,

D.E., and Wang, Q. (2015). A cluster randomised trial of cloth masks compared with medical masks

in healthcare workers. BJM Open *5*, e006577,10.1136/ bmjopen-2014-006577.

2. MacIntyre, C.R., Cauchemez, S., Dwyer, D.E., Seale, H., Cheung, P., Browne, G., Fasher, M., Gao,

Z., Booy, R., and Ferguson, N. (2009). Face Mask Use and Control of Respiratory Virus Transmission

in Households. Emerging Infectious Diseases *15*, 233-241,10.3201/eid1502.081167.

3. OSHA (1998). Respiratory Protection, Occupational Safety and Health Administration (OSHA),

Department of Labor, Washington, DC, USA,

4. ASTM (2019). Standard Specification for Performance of Materials Used in Medical Face Masks,

ASTM International, West Conshohocken, PA, USA,

5. ASTM (2017). Standard Test Method for Resistance of Medical Face Masks to Penetration by

Synthetic Blood (Horizontal Projection of Fixed Volume at a Known Velocity), ASTM International,

West Conshohocken, PA, USA,

6. ASTM (2019). Standard Test Method for Evaluation of the Bacterial Filtration Efficiency (BFE) of

Medical Face Mask Materials, Using a Biological Aerosol of *Staphylococcus aureus*, ASTM

International, West Conshohocken, PA, USA,

7. ASTM (2017). Standard Test Method for Determining the Initial Efficiency of Materials Used in Medical

Face Masks to Penetration by Particulates Using Latex Spheres, ASTM International, West

Conshohocken, PA, USA,

8. Rengasamy, S., Eimer, B., and Shaffer, R.E. (2010). Simple Respiratory Protection—Evaluation of the

Filtration Performance of Cloth Masks and Common Fabric Materials Against 20-1000 nm Size

Particles. Annals of Occupational Hygene *54*, 789-798

9. Cooper, D.W., Hinds, W.C., and Price, J.M. (1983). Emergency Respiratory Protection with Common

Materials. American Industrial Hygiene Association Journal *44*, 1-6

10. Konda, A., Prakash, A., Moss, G.A., Schmoldt, M., and Grant, G.D. (2020). Aerosol Filtration

Efficiency of Common Fabrics Used in Respiratory Cloth Masks. ACS

Nano,https://dx.doi.org/10.1021/acsnano.0c03252.

11. van der Sande, M., Teunis, P., and Sabel, R. (2008). Professional and Home-Made Face Masks

Reduce Exposure to Respiratory Infections among the General Population. PLoS ONE *3*, 1-6

12. Cooper, D.W., Hinds, W.C., Price, J.M., Weker, R., and Yee, H.S. (1983). Expedient Methods of

Respiratory Protection. II. Leakage Tests (Boston, MA: Harvard School of Public Health), pp. 47.

13. Brosseau, L.M., and Sietsema, M. (2020). Commentary: Masks-for-all for Covid-19 not based on

sounds data. University of Minnesota. https://www.cidrap.umn.edu/news-

perspective/2020/04/commentary-masks-all-covid-19-not-based-sound-data (May 14,2020).

14. Labor, U.S.D.o. (2004). Occupation Safety and Health Standards, Occupational Safety and Health

Administration, Washington, DC,

15. Incorporated, T. (2003). PortaCout Plus Model 8020: Operation and Service Manual (Shoreview, MN:

TSI Incorporated).

16. Incorporated, T. (2002). Model 8026 Particle Generator: Operation and Service Manual (Shoreview,

MN: TSI Incorporated).

17. Farra, Y.M., Eden, M.J., Coleman, J.R., Kulkarni, P., Ferris, C.F., Oakes, J.M., and Bellini, C. (2020).

Acute neuroradiological, behavioral, and physiological effects of nose-only exposure to vaporized

cannabis in C57BL/6 mice. Inhalation Toxicology,10.1080/08958378.2020.1767237.

SUPPLEMENTAL INFORMATION

Table SI1. Mask details, mean filtration efficiency ($\bar{x}$), standard deviation of mean filtration efficiency between replicates* (s_r), and standard deviation of filtration efficiencency over one minute runs (s_t).

Sample	Description	Mask worn as designed			Mask worn with nylon overlayer		
		$\bar{x}$	s_r	s_t	$\bar{x}$	s_r	s_t
N95-1	3M N95 model 1860	99.2%	0.4%	0.8%	-	-	-
N95-2	Makrite model 9500-N95	90.6%	5.9%	4.6%	95.2%	0.9%	4.7%
S-1	3M surgical mask model 1826	74.6%	4.1%	9.5%	90.3%	1.5%	3.9%
S-2	Keystone surgical mask model FM-EL-BLUE	59.3%	3.3%	13.0%	86.0%	3.2%	2.7%
S-3	Hong Da Wei Cai surgical mask labele for medical use	53.4%	4.4%	12.6%	90.0%	6.0%	5.6%
O-1	surgical style 4 layer mask with black "charcoal" layer (no brand information available)	73.4%	4.1%	9.7%	86.8%	0.4%	5.2%
CS-1	cloth surgical-style mask with earloops and wired nose bridge, layers (3): two cotton quilting fabric and one Pellon interfacing	58.6%	5.0%	11.6%	77.5%	6.2%	0.8%
CS-2	fabric surgical style mask with earloops, no wire at bridge of nose, layers: two cotton plainweave	28.2%	5.9%	24.3%	73.2%	1.4%	1.2%
CS-3	fabric surgical style mask with ties, wired nose bridge, layers (6): two Smartfab nonwoven fabric, two disposable baby wipe (dry), one massage table non-woven fabric cover, one meltblown filter (BFE85)	85.0%	1.3%	5.4%	81.3%	3.4%	7.9%
CS-4	fabric surgical style mask with ties, wired nose bridge, layers (2): two cotton duck	72.9%	8.8%	7.1%	78.5%	12.3%	6.7%
CS-5	nose, layers (2): two layers of cotton twill (sold by Reformation clothing company at thereformation.com)	56.0%	3.9%	13.1%	66.9%	1.7%	10.2%
CS-6	fabric surgical style mask with earloops, no wire at bridge of nose, layers (2): woven nylon	47.1%	2.3%	12.2%	56.8%	5.9%	8.7%
CC-1	commercially produce nuisance dust mask with cloth liner, layers (4): two Smartfab nonwoven fabric , one disposable baby wipe (dry), one meltblown filter (BFE84)	85.9%	6.3%	4.7%	89.3%	1.5%	3.8%
CC-2	comercially produced nuisance dust mask	60.3%	3.2%	10.4%	61.1%	2.8%	9.4%
CC-3	fabric cone-shaped mask with elastic head band and wired nose bridge, layers (6): two cotton muslin fabric, two disposable baby wipe (dry), one massage tablecover non-woven fabric, one meltblown filter (BFE85)	86.2%	1.0%	5.5%	88.5%	0.9%	3.8%
CC-4	fabric cone-shaped mask with elastic head band, layers (6): two Smartfab nonwoven fabric, two disposable baby wipe (dry), one massage table non-woven fabric cover, one meltblown filter (BFE85)	89.1%	1.7%	3.4%	91.7%	2.8%	4.3%
CC-5	fabric cone-shaped mask with elastic head band, wired nose bridge, PM2.5 filter insert, layers (4,including pocket): three cotton muslin, one masage table non-woven fabric cover	80.2%	2.5%	7.1%	84.3%	2.5%	5.9%
CC-6	fabric cone-shaped mask with elastic head band, layers (5): two Smartfab nonwoven fabric, one massage table non-woven fabric cover, two meltblown filter (BFE85)	90.7%	0.8%	3.1%	91.5%	1.1%	3.1%
CC-7	fabric con-shaped mask with elastic head band, wired nose bridge, layers (4): two Smartfab nonwoven, one massage table non-woven fabric cover, two meltblown filter (BFE85)	85.3%	2.2%	4.6%	87.2%	0.9%	4.4%
CC-8	fabric cone-shaped mask with two sets of ties, wired nose bridge, layers (3): two cotton fabric, one non-woven polypropylene (recycled grocery bag)	82.6%	1.2%	5.7%	81.3%	2.4%	8.5%
CD-1	duck-bill shaped mask with elastic head band, wired nose bridge, layers (6): 4 cotton fabric, 2 Pellon interfacing	64.2%	11.0%	9.5%	80.2%	1.8%	6.3%
N only	woven nylon stocking	7.0%	2.5%	18.0%	-	-	-

407 * n=4 replicates for mask CS-1, all other masks n=3 replicates

409 Figure S1. Two TSI PortaCount model 8028 used in this work. Sample tubes are of equal length and are

410 connected to right-hand ports labeled "sample". Instruments were operated in count mode with "Mask"-

411 labeled instrument sampling air from inside the mask and "Ref"-labeled instrument sampling ambient air

412 just outside of the mask.

N95-1	**N95-2**	**S-1**	**S-2**
O-1	**CS-1**	**CS-2**	**CS-3**
CS-4	CS-5	CS-6	CC-1
CC-2	**CC-3**	**CC-4**	**CC-5**
CC-6	**CC-7**	**CC-8**	**CD-1**

415   Figure S2. Gallery of mask images. Masks ordered by sample ID. Descriptions included in Table S1.

417   Additional and updated results are available through a web portal at masktestingatNU.com.