Is the Current N95 Respirator Filtration Efficiency Test Sufficient for Evaluating Protection Against Submicrometer Particles Containing SARS-CoV-2?

Changjie Cai[1,*], Evan L. Floyd[1], Kathleen A. Aithinne[1], Toluwanimi Oni[1]

[1]Department of Occupational and Environmental Health, University of Oklahoma Health Sciences Center, University of Oklahoma, Oklahoma City, Oklahoma 73104, USA

To be submitted to:

Revised on May 14, 2020

Abstract

Previous researchers measured the Overall Filtration Efficiency using sodium chloride testing aerosol with aerosol photometer to analyze the reuse of respirators after sterilization. However, this study showed that the Overall Filtration Efficiency would significantly overestimate the respirators' ability to protect against submicrometer particles containing SARS-CoV-2. For example, after three cycle H_2O_2 vaporous sterilizations, the most penetrating particle size for the N95 level respirators was from 250 nm – 500 nm, which carried the peak concentration of the SARS-CoV-2 in hospitals. The Size Specific Filtration Efficiency (250 nm – 500 nm) dropped to 56%±4%, however, the Overall Filtration Efficiency was still 86%±5%. In order to protect health care personnel adequately, we recommend measuring the Size Specific Filtration Efficiency to evaluate the reuse of respirators.

Keywords: N95, Size Specific Filtration Efficiency, Overall Filtration Efficiency,

Submicrometer Particles, SARS-CoV-2

Introduction

Recent studies indicates that aerosol transmission of the severe acute respiratory

syndrome coronavirus 2 (SARS-CoV-2) is plausible since the virus can remain viable and

infectious in aerosol form for hours (*1,2*). The actual SARS-CoV-2 size ranges from 60 nm –

150 nm (*3,4,5*). The peak concentration of the SARS-CoV-2 in hospitals was found in 250

nm – 500 nm particles (*6*). Due to the COVID-19 pandemic and shortage of mask supplies

(*7*), some studies analyzed the reuse of N95/KN95 masks after sterilization by measuring the

filtration efficiency using sodium chloride (NaCl) test aerosol (*8,9*). The N95 grade mask

should have a minimum filtration efficiency of 95% for 300 nm NaCl aerosols. The light-

scattering instruments (e.g., aerosol photometer), which are commonly used for filtration

efficiency test, are usually limited to measuring aerosol size from 100 nm to 10 µm.

However, the count median diameter of the NaCl test aerosol is 75±20 nm with the geometric

standard deviation ≤1.86 from the U.S. Centers for Disease Control and Prevention (CDC)

National Institute of Occupational Safety and Health (NIOSH) procedure No. TEB-APR-

STP-0059, meaning around **97.4%** particles are ≤250 nm, and around **92.4%** particles are

from 100 nm – 250 nm, which is not in the particle size range of containing the peak

concentration of the SARS-CoV-2 in hospitals. Therefore, a mask efficient for particles ≤

250 nm may not capture most SARS-CoV-2, and the size specific filtration efficiency is a

46   better assessment of the mask's protection ability rather than the overall filtration efficiency

47   to prevent the SARS-CoV-2 transmit via airborne particles. The goal of this demonstration

48   study was to test the effects of multiple sterilization cycles on the size specific filtration

49   efficiency compared to the overall filtration efficiency of KN95 and N95 masks.

Methods

We compared the effects of two- and three-cycle sterilization using vaporous

hydrogen peroxide (H_2O_2) and ultraviolet (UV) germicidal irradiation on the filtration

efficiencies by size of KN95 (Civilian Antivirus, Qingdao, Shandong, China) and N95

(model 1860, 3M, St Paul, MN, USA) mask. The experimental setup was illustrated in

previous study (_10_). A NaCl aerosol was generated using a Collision Nebulizer (3 jet, CH

Technologies, Westwood, NJ, USA) operated at 20 psi using 2% NaCl recommended by

NIOSH procedure No. TEB-APR-STP-0059. We tested five samples for each mask. A

scanning mobility particle sizer (SMPS, model 3936, TSI Inc., Shoreview, MN, USA) was

used to measure the number concentration of test aerosol from 16.8 nm to 514 nm up and

down stream of each sample. We conducted a two-sample t-test (with $\alpha=0.05$ as significance

threshold) to compare the mean filtration efficiency of the five samples at each aerosol size

between two and three sterilization cycles.

Results

The effects of multi-cycle sterilization on the filtration efficiency by aerosol size are

summarized in the **Figure 1**. After three H_2O_2 sterilization cycles, the filtration efficiency for

250 nm – 500 nm particles dropped from 84%±2% to 68%±3% for KN95, and from 97%±2%

to 56%±4% for N95. The differences between two and three cycles were significant for both

KN95 (*p*-value = 0.028±0.037) and N95 (*p*-value = 0.0009±0.0008). After UV sterilization,

the filtration efficiency of KN95 for 250 nm – 500 nm particles was 94.4%±1.0% after two

cycles, and 95.0%±0.6% after three cycles; and the filtration efficiency of N95 was

95.9%±1.4% after two cycles, and 96.9%±0.7% after three cycles. The differences were not

statistically significant between two and three cycles for both KN95 (*p*-value = 0.754±0.187)

and N95 (*p*-value = 0.448±0.267).

Figure 1. Effects of multi-cycle sterilization on filtration efficiency by aerosol size using

H2O2 and UV treatment for (a) N95, and (b) KN9.

Table 1. Comparison of overall filtration efficiency and size specific (250 nm – 500 nm)

filtration efficiency after multi-cycle H2O2 treatment.

Mask Type	H2O2 Treatment	Overall Filtration Efficiency	Size Specific Filtration Efficiency

KN95 – Civilian Antivirus Mask	2 Cycle	93%±3%	84%±2%
	3 Cycle	90%±3%	68%±3%
N95 – 3M 1860 Mask	2 Cycle	98%±1%	97%±2%
	3 Cycle	86%±5%	56%±4%

The size specific filtration efficiency is quite different from the overall filtration efficiency, especially after three cycle H_2O_2 treatment (see the **Table 1**). For instance, the overall filtration efficiencies for KN95 and N95 after three cycle H_2O_2 treatment are 90%±3% and 86%±5%, respectively; however, the size specific filtration efficiencies are only 68%±3% for KN95 and 56%±5% for N95, respectively.

Discussion

This study proposed that, in addition to considering the overall filtration efficiency, the filtration efficiencies for particle sizes similar to infectious particles should be considered. This study also found that the two different multi-cycle sterilization processes have unique effects on the filtration efficiencies by aerosol size of different masks. Multi-cycle sterilization with UV appears to have fewer negative effects than H_2O_2. Limitations include the small variety of mask manufacturers and the limited numbers of samples (n=5) for each mask and only two sterilization techniques evaluated. In addition, this study only evaluated the filtration efficiency after three sterilization cycles as this corresponds with guidance from

the American College of Surgeons for H_2O_2 sterilization. The filter material might degrade

further with more cycles, which should be investigated for UV treatment.

Acknowledgement

This work was made possible by support from the Oklahoma State Department of

Health to establish this testing program, by the supply chain logistics group at the University

of Oklahoma Medical Center who provided the respirators and sterilization treatments, by the

University of Oklahoma Health Sciences Center VPR's office through a COVID19 Rapid

Response pilot grant, and by the student volunteers that assisted with data collection.

References

1. van Doremalen N, Bushmaker T, Morris DH, Holbrook MG, Gamble A, Williamson BN, et al. Aerosol and surface stability of SARS-CoV-2 as compared with SARS-CoV-1. New England Journal of Medicine. 2020; DOI: 10.1056/NEJMc2004973

2. Asadi S, Bouvier N, Wexler AS, & Ristenpart WD. The coronavirus pandemic and aerosols: Does COVID-19 transmit via expiratory particles? Aerosol Science and Technology, 2020; 54(6), 635-638.

3. Kim JM, Chung YS, Jo HJ, Lee NJ, Kim MS, Woo SH, et al. Identification of Coronavirus Isolated from a Patient in Korea with COVID-19. Osong Public Health and Research Perspectives. 2020; 11(1), 3.

4. Cascella M, Rajnik M, Cuomo A, Dulebohn SC, & Di Napoli R. Features, evaluation and treatment coronavirus (COVID-19). In Statpearls [internet]. StatPearls Publishing. 2020

5. Matsuyama S, Nao N, Shirato K, Kawase M, Saito S, Takayama I, et al. Enhanced isolation of SARS-CoV-2 by TMPRSS2-expressing cells. Proceedings of the National Academy of Sciences. 2020; 117(13), 7001-7003.

6. Liu Y, Ning Z, Chen Y, Guo M, Liu Y, Gali NK, et al. Aerodynamic analysis of SARS-CoV-2 in two Wuhan hospitals. Nature. 2020; https://doi.org/10.1038/s41586-020-2271-3

7. Ranney ML, Griffeth V, Jha AK. Critical Supply Shortages — The Need for Ventilators and Personal Protective Equipment during the Covid-19 Pandemic. New England Journal of Medicine. 2020; DOI: 10.1056/NEJMp2006141

8. Viscusi DJ, Bergman MS, Eimer BC, & Shaffer RE. Evaluation of five

decontamination methods for filtering facepiece respirators. Annals of occupational

hygiene. 2009; 53(8), 815-827.

9. Liao L, Xiao W, Zhao M, Yu X, Wang H, Wang Q, et al. Can N95 respirators be

reused after disinfection? And for how many times?. ACS nano. (2020)

10. Cai C, Floyd E. Effects of sterilization on the filtration efficiency of KN95 and

surgical face masks. (2020)

Figure/Table Legends

Figure 1. Effects of multi-cycle sterilization on filtration efficiency by aerosol size using
H_2O_2 and UV treatment for (a) N95, and (b) KN95

Table 1. Comparison of overall filtration efficiency and size specific (250 nm – 500 nm)
filtration efficiency after multi-cycle H_2O_2 treatment.