

Filtration efficiency test

			0,3µm	0,5µm	3,0µm	
Unsterilised material (from package)	White layer only	Sample 1 (n = 4)	3/4/2020	60.84%	78.59%	95.90%
		Sample 2 (n = 4)	3/4/2020	64.29%	82.02%	96.45%
			Averaged	62.57%	80.30%	96.17%
			Intersample Standard Dev.	2.44%	2.43%	0.39%
	Blue layer only	Sample 3 (n = 4)	3/4/2020	62.28%	78.95%	96.16%
		Sample 4 (n = 4)	3/4/2020	63.40%	80.09%	96.72%
			Averaged	62.84%	79.52%	96.44%
			Intersample Standard Dev.	0.79%	0.81%	0.39%
	Single Layer	Sample 5(n = 4)	3/4/2020	70.42%	90.17%	99.65%
		Sample 6 (n = 4)	3/4/2020	69.74%	89.19%	99.84%
			Averaged	70.08%	89.68%	99.74%
			Intersample Standard Dev.	0.48%	0.70%	0.13%
	Double Layer	Sample 7 (n = 4)	3/4/2020	87.99%	98.35%	99.98%
		Sample 8 (n = 4)	3/4/2020	87.38%	98.21%	99.98%
			Averaged	87.68%	98.28%	99.98%
			Intersample Standard Dev.	0.43%	0.10%	0.00%
Double Layer, reversed	Sample 9 (n = 4)	3/4/2020	89.29%	98.50%	99.98%	
	Sample 10 (n = 4)	3/4/2020	88.27%	98.20%	100.00%	
		Averaged	88.78%	98.35%	99.99%	
		Intersample Standard Dev.	0.72%	0.22%	0.01%	
Double Layer, after use 20 minutes	Sample 11 (n = 4)	3/4/2020	90.97%	99.08%	100.00%	
	Sample 12 (n = 4)	3/4/2020	90.90%	99.07%	100.00%	
		Averaged	90.93%	99.07%	100.00%	

Steam Sterilised (5min, 134 degrees Celsius, 2 atm)

			Intersample Standard Dev.	0.05%	0.00%	0.00%
Triple layer	Sample 13 (n = 4)	3/4/2020	94.10%	99.51%	99.98%	
	Sample 14 (n = 4)	3/4/2020	93.58%	99.39%	100.00%	
			Averaged	93.84%	99.45%	99.99%
			Intersample Standard Dev.	0.37%	0.08%	0.01%
Single Layer, 1x sterilized	Sample 15 (n = 4)	3/4/2020	66.15%	87.14%	99.40%	
	Sample 16 (n = 4)	3/4/2020	66.58%	87.24%	99.73%	
			Averaged	66.37%	87.19%	99.57%
			Intersample Standard Dev.	0.31%	0.07%	0.23%
Double Layer, 1x sterilized	Sample 17 (n = 4)	3/4/2020	80.63%	95.91%	100.00%	
	Sample 18 (n = 4)	3/4/2020	80.16%	95.67%	99.98%	
			Averaged	80.39%	95.79%	99.99%
			Intersample Standard Dev.	0.33%	0.17%	0.01%
Triple layer, 1x sterilized	Sample 19 (n = 4)	3/4/2020	87.98%	98.35%	99.96%	
	Sample 20 (n = 4)	3/4/2020	88.57%	98.52%	99.98%	
	Sample 21 (n = 4)	12/5/2020	82.74%	98.94%	99.91%	
	Sample 22 (n = 4)	12/5/2020	83.71%	99.02%	99.97%	
	Sample 23 (n = 4)	12/5/2020	83.77%	98.98%	99.99%	
	Sample 24 (n = 4)	12/5/2020	83.91%	98.95%	99.97%	
			Averaged	85.11%	98.44%	99.97%
			Intersample Standard Dev.	2.49%	0.28%	0.03%
Triple layer, 2x sterilized	Sample 25 (n = 4)	12/5/2020	89.08%	99.52%	99.97%	
	Sample 26 (n = 4)	12/5/2020	86.52%	99.26%	99.93%	
	Sample 27 (n = 4)	12/5/2020	87.97%	99.42%	99.97%	
	Sample 28 (n = 4)	12/5/2020	86.51%	99.31%	99.96%	
			Averaged	87.52%	99.38%	99.96%
			Intersample Standard Dev.	1.25%	0.12%	0.02%

	Triple layer, 3x sterilized	Sample 29 (n = 4)	12/5/2020	81.71%	98.74%	99.97%
		Sample 30 (n = 4)	12/5/2020	82.88%	98.94%	99.92%
		Sample 31 (n = 4)	12/5/2020	83.66%	99.01%	99.97%
		Sample 32 (n = 4)	12/5/2020	82.07%	98.80%	99.99%
	Averaged			82.58%	98.87%	99.97%
	Intersample Standard Dev.			0.87%	0.12%	0.03%
	Triple layer, 4x sterilized	Sample 33 (n = 4)	12/5/2020	86.00%	99.27%	99.96%
		Sample 34 (n = 4)	12/5/2020	86.36%	99.29%	99.90%
		Sample 35 (n = 4)	12/5/2020	85.60%	99.21%	99.97%
		Sample 36 (n = 4)	12/5/2020	85.27%	99.17%	99.92%
	Averaged			85.81%	99.23%	99.94%
	Intersample Standard Dev.			0.47%	0.05%	0.03%
	Triple layer, 5x sterilized	Sample 37 (n = 4)	12/5/2020	83.61%	99.00%	99.95%
		Sample 38 (n = 4)	12/5/2020	84.71%	99.16%	99.98%
		Sample 39 (n = 4)	12/5/2020	83.19%	98.98%	99.96%
		Sample 40 (n = 4)	12/5/2020	82.42%	98.88%	99.99%
	Averaged			83.48%	99.00%	99.97%
	Intersample Standard Dev.			0.96%	0.11%	0.02%
Comparison with commercial Masks & Respirators	Surgical Mask	Sample 41	12/5/2020	55.89%	89.26%	98.96%
		Sample 42	12/5/2020	51.48%	87.47%	98.01%
		Sample 43	12/5/2020	57.64%	89.86%	99.48%
		Sample 44	12/5/2020	53.07%	87.84%	99.22%
	Averaged			54.52%	88.61%	98.92%
	Intersample Standard Dev.			2.77%	1.13%	0.64%
	Disposable Face Mask FFP2	Sample 45	12/5/2020	93.55%	99.52%	100.00%
		Sample 46	12/5/2020	93.93%	99.58%	100.00%
		Sample 47	12/5/2020	94.35%	99.61%	100.00%
		Sample 48	12/5/2020	94.47%	99.57%	100.00%

			Averaged	94.08%	99.57%	100.00%
			Intersample Standard Dev.	0.42%	0.04%	0.00%
3M 8320 FFP2 NR D Mask	Sample 49	12/5/2020	98.91%	99.90%	99.91%	
	Sample 50	12/5/2020	95.91%	99.65%	100.00%	
	Sample 51	12/5/2020	98.10%	99.78%	100.00%	
	Sample 52	12/5/2020	96.84%	99.65%	99.83%	
			Averaged	97.44%	99.75%	99.94%
			Intersample Standard Dev.	1.33%	0.12%	0.08%